



## TEST REPORT

No. : SHIN190601677CCM

Date : Jun. 10, 2019

Page: 1 of 4

CUSTOMER NAME: SunlightSeal

ADDRESS: Chris Broersestraat 9 2742 MW Waddinxveen

The test results are copied from report No.: SHINCCM190501542CCM dated: Jun. 10, 2019 issued by SGS.

Sample Name : HIGH PERFORMANCE TRANSPARENT HEAT INSULATION GLASS COATING

Manufacturer : SunlightSeal

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

\*\*\*\*\*

Test Required : Please see the next page(s)

Test Method : GB/T 2680-94

Date of Receipt : May. 28, 2019

Testing Start Date : May. 28, 2019

Testing End Date : Jun. 10, 2019

Test result(s) : For further details, please refer to the following page(s)  
(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for  
SGS-CSTC Standards  
Technical Services

---

Tiffany Liu  
Authorized signatory



*Sunlightseal, de energiebesparende  
glascoating!*

## TEST REPORT

No. : SHIN190601677CCM

Date : Jun. 10, 2019


Page: 2 of 4

### Summary of Result(s):

No.	Test Item	Test Method	Test Result	Conclusion
1	Light transmittance	GB/T 2680-94 section 3.1	75.01%	/
2	Sheltering coefficient	GB/T 2680-94 section 3.9	0.59	/
3	UV-transmittance	GB/T 2680-94 section 3.10	0.16%	/

Note: Pass: Meet the requirements;  
 Fail: Does not meet the requirements;  
 /: Not Apply to the judgment.

### Original sample photo(s):



*Sunlightseal, de energiebesparende  
 glascoating!*

## TEST REPORT

No. : SHIN190601677CCM

Date : Jun. 10, 2019

Page: 3 of 4

1. Test item: Light transmittance

Test method: GB/T 2680-94 section 3.1

Test condition:

Specimen: 100mm×100mm×3.3mm, 1pc

Lab environmental condition: 23±2°C, 50±5%RH

Test result:

Test Item	Test Result
Light transmittance (%)	75.01

2. Test item: Sheltering coefficient

Test method: GB/T 2680-94 section 3.9

Test condition:

Specimen: 100mm×100mm×3.3mm, 1pc

Lab environmental condition: 23±2°C, 50±5%RH

Test result:

Test Item	Test Result
Sheltering coefficient	0.59



*Sunlightseal, de energiebesparende  
glascoating!*

## TEST REPORT

No. : SHIN190601677CCM

Date : Jun. 10, 2019

Page: 4 of 4

3. Test item: UV-transmittance

Test method: GB/T 2680-94 section 3.10

Test condition:

Specimen: 100mm×100mm×3.3mm, 1pc

Lab environmental condition: 23±2°C, 50±5%RH

Test result:

Test Item	Test Result
UV-transmittance (%)	0.16

The test report is an English version of report No.: SHIN190601677CCM\_CN dated: Jun. 10, 2019 issued by SGS, this report is for reference only.

\*\*\*\*\* End of report\*\*\*\*\*

In the territory of The Netherlands, the test report without CMA logo expresses the test report shall only be used for client scientific research, teaching, internal quality control, product research and development, etc...and just for client internal reference.



*Sunlightseal, de energiebesparende  
glascoating!*